

Heavy Slack Wax Grade 8 & 16

Specification	Method	Value
Oil Content (%)	ASTM D721	8-16 & 16-23
Viscosity @100°C (cSt)	ASTM D445	5.0-7.0
Color	ASTM D1500	Max 2
Melting Point (°C)	ASTM D87	45-65
Flash Point	ASTM D93	Min 195

Light Slack Wax Grade 8 & 16

Specification	Method	Value
Oil Content (%)	ASTM D721	8-16 & 16-23
Viscosity @100°C (cSt)	ASTM D445	Max 5
Color	ASTM D1500	Max 2
Melting Point (°C)	ASTM D87	45-65
Flash Point	ASTM D93	Min 195

Unbleached Heavy & Light Paraffin Wax Group II

Specification	Method	Value
Oil Content (%)	ASTM D721	Max 3.5
RI @70°C	ASTM D1218	1.43-1.445
Color	ASTM D1500	Max 1
Melting Point (°C)	ASTM D87	45-75
ASh(%)	ASTM D482	Max 0.03

Unbleached Heavy & Light Paraffin Wax Group III

Specification	Method	Value
Oil Content (%)	ASTM D721	Max 8
RI @70°C	ASTM D1218	1.43-1.445
Color	ASTM D1500	Max 1
Melting Point (°C)	ASTM D87	45-75
ASh(%)	ASTM D482	Max 0.03

Residue Wax (Foots Oil)

Specification	Method	Value
Viscosity Index	ASTM D2270	90
Viscosity @100°C (cSt)	ASTM D445	7.42
Color	ASTM D1500	Max 3
Flash Point	ASTM D93	218



Heavy Extract (RPO)

Specification	Method	Value
Viscosity @100°C (cSt)	ASTM D445	28-100
Flash Point	ASTM D93	Min 210
Aniline Point	ASTM D611	22-45
Color	ASTM D1500	Min 8
SP.gr @15.5°C	ASTM D1298	0.8-1.6
RI @70°C	ASTM D1218	1.4-1.6

Light Extract (RPO)

Specification	Method	Value
Viscosity @100°C (cSt)	ASTM D445	3.0-28
Flash Point	ASTM D93	Min 200
Aniline Point	ASTM D611	22-45
Color	ASTM D1500	Min 8
SP.gr @15.5°C	ASTM D1298	0.8-1.1
RI @70°C	ASTM D1218	1.4-1.6

Base Oil SN150

Specification	Method	Value
Viscosity @100°C (cSt)	ASTM D445	5-6.2
Viscosity @40°C (cSt)	ASTM D445	Report
VI	ASTM D2270	Min 95
Flash Point	ASTM D93	Min 200
Color	ASTM D1500	Max 1.5
SP.gr @15.5°C	ASTM D1298	0.87-0.88
Pour Point (°C)	ASTM D97	Max -6

Base Oil SN500

Specification	Method	Value
Viscosity @100°C (cSt)	ASTM D445	10.30-11.2
Viscosity @40°C (cSt)	ASTM D445	Report
VI	ASTM D2270	Min 88
Flash Point	ASTM D93	Min 230
Color	ASTM D1500	Max 2.0
SP.gr @15.5°C	ASTM D1298	0.88
Pour Point (°C)	ASTM D97	Max -3

